

USSN 09/840,859

Amendments to the Claims:

This listing of claims replaces all prior versions, and listing, of claims in the application.

Listing of Claims:

1. (Currently amended) A fastening device for promoting the assembly and adherence of associated pieces upon exposure to electromagnetic energy, comprising a susceptor sheet and a heat-activatable adhesive on at least one surface of said susceptor, wherein the pattern of the heat-activatable adhesive on the surface of the susceptor is such that a) when a test surface congruent in shape to the susceptor surface is placed over the susceptor with the adhesive intermediate and in contact with the susceptor and the test surface, at least about 35% of the area of surface contact between the adhesive and said test surface can have inscribed within it circles having a diameter of from about 1/2" to about 0.001", and b) from about 0.001% to about 65% of the surface area of the susceptor is in contact with said adhesive, and c) from about 0.05% to about 65% of the total area of the test surface is in contact with the adhesive as measured by the post-bonding test procedure defined herein.
2. (Previously presented) The fastening device according to Claim 1 wherein at least about 35% of the area of surface contact between the adhesive and said test surface can have inscribed within it circles having a diameter of about 1/4" to about 0.001".
3. (Original) The fastening device according to Claim 2 wherein the susceptor has a thickness of no greater than about 2 mils.
4. (Currently amended) The fastening device according to Claim 13 wherein from about 0.001% to about 65% of the surface area of the test surface is in pre-bonding contact with the adhesive.

USSN 09/840,859

5. (Currently amended) The fastening device according to Claim 4~~1~~ wherein the adhesive is applied in a discontinuous manner.
6. (Currently amended) The fastening device according to Claim 5~~1~~ wherein at least about 35% of the area of surface contact between the adhesive and the susceptor surface can have inscribed within it circles having a diameter of  $\frac{1}{4}$ " to about 0.001".
7. (Currently amended) The fastening device according to Claim 6~~1~~ wherein at least about 35% of the area of surface contact between the adhesive and the susceptor surface can have inscribed within it circles having a diameter of about  $\frac{1}{4}$ " to about 0.001".
8. (Previously presented) The fastening device according to Claim 7 wherein from about 0.001% to about 30% of the surface area of the susceptor is in contact with the adhesive.
9. (Currently amended) The fastening device according to Claim 6~~1~~ wherein the area of surface contact between the adhesive and the test surface is less than the area of surface contact between the adhesive and the susceptor.
10. (Cancelled)
11. (Currently amended) The fastening device according to Claim 4~~0~~ ~~1~~ additionally comprising a supplemental layer having a thickness of up to about 10 mils between the susceptor and the adhesive.
12. (Original) The fastening device according to Claim 11 wherein the supplemental layer is selected from the group consisting of insulation, foam, a continuous layer of adhesive, scrim, a paper material, a thermoplastic material, and mixtures thereof.
13. (Original) The fastening device according to Claim 12 wherein the supplemental layer is a continuous layer of adhesive.

USSN 09/840,859

14. (Currently amended) The fastening device according to Claim ~~101~~ which additionally comprises a primer located on the surface of the susceptor sheet between the susceptor and the adhesive layer.
15. (Currently amended) The fastening device according to Claim ~~101~~ wherein at least about 50% of the area of surface contact between the adhesive and said test surface can have inscribed within it circles having a diameter of about 1/4" to about 0.001"; from about 0.001% of to about 15% of the surface area of the test surface is in pre-bonding contact with the adhesive; and from about 1% to about 35% of the total area of the test surface is in contact with the adhesive, as measured by the post-bonding test procedure defined herein.
16. (Currently amended) The fastening device according to Claim ~~101~~ wherein the susceptor is ~~activateable~~activatable by induction heating.
17. (Original) The fastening device according to Claim 16 wherein the susceptor is ~~activateable~~activatable by frequencies of about 1,000 kHz or less.
18. (Original) The fastening device according to Claim 17 wherein the susceptor is selected from metallic foils and non-metallic foils.
19. (Currently amended) The fastening device according to Claim ~~101~~ wherein the susceptor's surface is textured.
20. (Currently amended) The fastening device according to Claim ~~101~~ wherein the susceptor's surface is perforated.
21. (Currently amended) The fastening device according to Claim ~~101~~ wherein the adhesive is selected from hot-melt adhesives, curable adhesives, and mixtures thereof.

USSN 09/840,859

22. (Original) The fastening device according to Claim 21 wherein the adhesive softens at a temperature of at least about 60°C.
23. (Original) The fastening device according to Claim 22 wherein the adhesive layer includes both hot-melt adhesive and pressure-activated adhesive.
24. (Currently amended) The fastening device according to Claim ~~10~~1 wherein the adhesive is selected from hot-melt adhesives, curable adhesives, and mixtures thereof.
25. (Original) The fastening device according to Claim 24 wherein the hot-melt adhesive is selected from polyamides, polyolefins, ethylene/vinyl acetate copolymers, and mixtures thereof.
26. (Original) The fastening device according to Claim 25 wherein the susceptor is a metallic foil comprising materials selected from the group consisting of metallic fibrous materials, conductive metal materials, conductive magnetic materials, and mixtures thereof.
27. (Original) The fastening device according to Claim 26 wherein the metallic foil is made from a metal selected from the group consisting of steel, copper, iron, nickel, tin, aluminum, and mixtures thereof.
28. (Original) The fastening device according to Claim 27 wherein the susceptor sheet has a thickness of no greater than about 1 mil.
29. (Original) The fastening device according to Claim 28 wherein the susceptor sheet is made from aluminum foil.
30. (Original) The fastening device according to Claim 22 wherein the adhesive is located on one surface of the susceptor sheet.

USSN 09/840,859

31. (Original) The fastening device according to Claim 22 wherein the adhesive is located on both surfaces of the susceptor sheet.
32. (Original) The fastening device according to Claim 22 wherein the adhesive is present on the susceptor sheet in the form of a web configuration selected from random webs, ordered webs, and mixtures thereof.
33. (Original) The fastening device according to Claim 22 wherein the adhesive is concentrated close to the edges of the susceptor.
34. (Original) The fastening device according to Claim 22 wherein the adhesive is present on the susceptor sheet in a discontinuous pattern.
35. (Original) The fastening device according to Claim 34 wherein the adhesive is placed on the susceptor sheet in a pattern selected from spots, lines, cones, pyramids, cylinders, cubes, spheres, donuts, stars, and mixtures thereof.
36. (Original) The fastening device according to Claim 22 formulated in the form selected from moldings, wall coverings, wallboard, laminates, carpeting, fabric and floor coverings.
37. (Original) The fastening device according to Claim 17 wherein the susceptor is selected from the group consisting of foils, agglomerated threads, agglomerated particles and mixtures thereof.
38. (Original) The fastening device according to Claim 22 activated by electromagnetic energy having a frequency of about 500 kHz or less.
39. (Currently amended) The fastening device according to Claim ~~22~~<sup>1</sup> wherein: at least about 50% of the area of surface contact between the adhesive and said test surface can have inscribed within it circles having a diameter of about 1/4" to about 0.001"; from

USSN 09/840,859

about 0.001% to about 15% of the surface area of the test surface is in pre-bonding contact with the adhesive; and from about 1% to about 35% of the total area of the test surface is in contact with the adhesive as measured by the post-bonding test procedure defined herein.

40. (Previously presented) The fastening device according to Claim 39 wherein at least about 50% of the area of surface contact between the adhesive and said test surface can have inscribed within it circles having a diameter of about 3/16" to about 0.001".
41. (Previously presented) The fastening device according to Claim 40 wherein at least about 75% of the area of surface contact between the adhesive and said test surface can have inscribed within it circles having a diameter of about 3/16" to about 0.001".
42. (Previously presented) The fastening device according to Claim 40 wherein from about 5% to about 25% of the total surface area of the test surface is in contact with the adhesive as measured by the post-bonding test procedure defined herein.
43. (Original) The fastening device according to Claim 22 which is substantially flat.
44. (Original) The fastening device according to Claim 35 wherein the adhesive decreases in cross-sectional area as one moves away from the susceptor and toward the surface to be bonded.
45. (Original) The fastening device according to Claim 12 wherein the supplemental layer is a continuous layer of adhesive and the adhesive is placed on top of that supplemental layer.
46. (Original) The fastening device according to Claim 45 wherein the adhesive is placed on top of the supplemental layer in the form of a web configuration selected from random webs, ordered webs, and mixtures thereof.

USSN 09/840,859

47. (Original) The fastening device according to Claim 46 wherein the susceptor is an aluminum foil.
48. (Original) The fastening device according to Claim 47 wherein the adhesive is a polyamide.
49. (Original) The fastening device according to Claim 47 wherein the adhesive is located on one face of the susceptor.
50. (Original) The fastening device according to Claim 47 wherein the adhesive is located on both faces of the susceptor.
51. (Original) The fastening device according to Claim 29 wherein the adhesive is placed on the susceptor in the form of a web configuration selected from random webs, ordered webs and mixtures thereof.
52. (Original) The fastening device according to Claim 51 wherein the adhesive is a polyamide.
53. (Original) The fastening device according to Claim 52 wherein the adhesive is located on one face of the susceptor.
54. (Original) The fastening device according to Claim 52 wherein the adhesive is located on both faces of the susceptor.
55. (Original) The fastening device according to Claim 54 in the form of a nestable tape.
56. (Original) The fastening device according to Claim 29 wherein the adhesive is present on the susceptor sheet in a discontinuous pattern selected from spots, lines, cones, pyramids, cylinders, cubes, spheres, stars and mixtures thereof.
57. (Original) The fastening device according to Claim 56 wherein the adhesive is a polyamide.

USSN 09/840,859

58. (Original) The fastening device according to Claim 57 wherein the adhesive is located on one side of the susceptor.

59. (Original) The fastening device according to Claim 57 wherein the adhesive is located on both sides of the susceptor.

60. (Currently amended) A fastening device for promoting the assembly and adherence of associated pieces upon exposure to electromagnetic energy, comprising a susceptor sheet having a thickness of no greater than about 2 mils and a heat-activatable adhesive on at least one surface of said susceptor, wherein the pattern of the heat-activatable adhesive is such that a) when a test surface congruent in shape to the susceptor surface is placed over the susceptor with the adhesive intermediate and in contact with the susceptor and the test surface, at least about 35% of the area of surface contact between the adhesive and said test surface can have inscribed within it circles having a diameter of  $\frac{1}{4}$ " to 0.001", and b) from about 0.001% to about 65% of the surface area of the susceptor is in contact with the adhesive, and c) from about 0.05% to about 65% of the total area of the test surface is in contact with the adhesive as measured by the post-bonding test procedure defined herein.

61. (Previously presented) The fastening device according to Claim 60 wherein at least about 35% of the area of surface contact between the adhesive and said test surface can have inscribed within it circles having a diameter of  $\frac{1}{4}$ " to about 0.001".

62. (Original) The fastening device according to Claim 61 wherein the susceptor has a thickness of no greater than about 2 mils.

63. (Currently amended) The fastening device according to Claim 62 ~~60~~ wherein from about 0.001% to about 30% of the surface area of the susceptor is in contact with the adhesive.



USSN 09/840,859

64. (Original) The fastening device according to Claim 63 wherein the contact between the adhesive and the surface to be bonded is discontinuous.

65. (Previously presented) The fastening device according to Claim 63 wherein at least about 35% of the area of surface contact between the adhesive and the susceptor can have inscribed within it circles having a diameter of  $\frac{1}{8}$ " to about 0.001".

66. (Previously presented) The fastening device according to Claim 65 wherein at least about 35% of the area of surface contact between the adhesive and the susceptor can have inscribed within it circles having a diameter of  $\frac{1}{8}$ " to about 0.001".

67–112. (Cancelled)

113. (Newly presented) A fastening device for promoting the assembly and adherence of associated pieces upon exposure to electromagnetic energy, comprising a susceptor sheet having a thickness of no greater than about 2 mils and a heat-activatable adhesive on at least one surface of said susceptor, wherein the pattern of the heat-activatable adhesive on the surface of the susceptor is such that a) when a test surface congruent in shape to the susceptor surface is placed over the susceptor with the adhesive intermediate and in contact with the susceptor and the test surface, at least about 35% of the area of surface contact between the adhesive and said test surface can have inscribed within it circles having a diameter of from about  $\frac{1}{8}$ " to about 0.001", b) from about 0.001% to about 65% of the surface area of the susceptor is in contact with said adhesive, c) from about 0.001% to about 65% of the surface area of the test surface is in pre-bonding contact with the adhesive, and d) from about 0.05% to about 65% of the total area of the test surface is in contact with the adhesive as measured by the post-bonding test procedure defined herein.